



 **Westermann**  
Sealing Products

*Quality. Trust. Confidence.*

[www.gowestermann.com](http://www.gowestermann.com)

# Materials and Styles



Quality. Trust. Confidence.

## Compressed Nonasbestos

Style #	Material	Color	Continuous Operating Temp °F	Continuous Pressure (psi)	Notes
Westermann CNA 1500	Aramid / NBR	Green	460	725	Water, Oil, Gas, Steam
Westermann CNA 1501	Aramid / SBR	Off White	490	725	Water, Oil, Gas, Steam
Westermann CNA 1502	Aramid / NBR	Black	518	1015	Water, Oil, Gas, Steam
Westermann CNA 1503	Inorganic / NBR	Grey	806	1480	Superheated Steam

## Elastomer \*

Style #	Material	Operating Temp °F	Pressure (psi)	Notes
S70	SBR	-20 to +180	250	General purpose air and water
S70P	Premium SBR	-20 to +200	250	ASTM D1330 Gr. 1 & 2
N60	Neoprene	-20 to +190	250	Non-aromatic gasoline and petroleum solvents
E60	EPDM	-20 to +250	250	Air, steam and mild acids
B60	NBR	-30 to +200	250	Oil and aromatic solvents
CI75	SBR / Cloth Insert	-20 to +180	250	Air and water
V70	Fluoroelastomer	-15 to +400	250	Acids, oils and gasoline
FDA60	White NBR	-30 to +200	250	Oily and greasy food substances

## PTFE

Style #	Material	Color	Operating Temp °F	Pressure (psi)	Notes
P61	Sintered PTFE	White	260	**	Hard PTFE / Aggressive acids and caustics
Fleur 2000	Modified PTFE	Blue	500	800	Aggressive mild acids and caustics
Fleur 2001	Modified PTFE	Fawn	500	1200	Aggressive strong acids
Fleur 2002	Modified PTFE	Off White	500	1200	Aggressive strong caustics
Fleur 2003	Expanded PTFE	White	500	**	Soft PTFE / Aggressive acids and caustics

## Graphite

Style #	Material	Operating Temp °F	Pressure (psi)	Notes
FG	Graphite - No insert	-400 to +750	1750	High heat, aggressive chemicals
FFG	Graphite - Foil insert	-400 to +750	1750	High heat, aggressive chemicals
TG	Graphite - Tang insert	-400 to +900	1400	High heat, aggressive chemicals

## Spiralwound

Style #	Material	Operating Temp °F	Pressure (psi)	Notes
Westermann WG	Graphite / 304SS	+482	**	Other materials and styles available

## High Temperature

Style #	Material	Operating Temp °F	Pressure (psi)	Notes
Milam PSS	High Quality Mica	+1652	**	Exhaust and hot, dry air applications

\* Garlock Styles Available

### Limitation of Liability:

The information contained herein is typical and should not be considered a recommendation. Specific applications require an in-depth engineering review. Failure to select proper products could result in failure resulting in loss of property and or personal injury.

**Westermann Bolt & Gasket**  
 4300 Diplomacy Rd  
 Fort Worth, TX 76155  
 Phone 800-434-9954  
 972-314-4900  
 Fax 972-314-4906  
 www.gowestermann.com